## Balmoral



| $\bigcirc$ |  |
|------------|--|
|            |  |





**Technical Data** 

ROLLER F



| Composition      | 100% Polyester   |  |  |  |  |
|------------------|--|--|--|--|--|
| Width            | Blockout: 3,000mm, 127mm & 89mm   Light Filtering: 3,000mm   |  |  |  |  |
| Weight           | Blockout 390gsm +/-5%   Light filtering 220gsm +/-5%   |  |  |  |  |
| Thickness        | Blockout 0.60mm +/-5%   Light filtering 0.55mm +/-5%   |  |  |  |  |
| Opacity/Openness | Blockout tested to AS-2663-1999  |  |  |  |  |
| Light Fastness   | ≥ 5 (Blue wool scale)  |  |  |  |  |
| Coating          | Blockout coated with acrylic foam   Light filtering stiffened with acrylic   |  |  |  |  |
| Flame Retardant  | Product is designed and manufactured to comply with Building Code of Australia requirements for class 2 to 9 buildings |  |  |  |  |
| Cleaning         | Surface dust can be removed with vacuum or a soft cloth  |  |  |  |  |









5 YEAR WARRANTY

BLOCKOUT LIGHT FILTERING

PVC FREE

ECO

FRIENDLY





## **Solar Properties**

|                |    | European standard tested to<br>DIN EN 410: 2011 |    |            |     |     | Tested to EN 14501  |   |  |
|----------------|----|---|----|------------|-----|-----|---|---|--|
|                | Ts | Rs  | As | Tv/<br>Vit | Tuv | 0-F | Single Glass<br>Reference Glazing A<br>[g window 0.85]<br>[U window 5.7]<br>g-total | High Performance Glass<br>Reference Glazing D<br>[g window 0.32]<br>[U window 1.1]<br>g-total |  |
| Blockout       | 0  | 83  | 17 | 0          | 0   | 0   | 0.23  | 0.23  |  |
| White LF       | 46 | 54  | 0  | 47         | 33  | 4   | 0.46  | 0.26  |  |
| Dove LF        | 25 | 34  | 41 | 21         | 15  | 3   | 0.55  | 0.28  |  |
| Concrete LF    | 37 | 42  | 21 | 34         | 24  | 4   | 0.52  | 0.27  |  |
| Pearl LF       | 46 | 53  | 1  | 47         | 34  | 4   | 0.47  | 0.27  |  |
| Birch LF       | 40 | 48  | 12 | 39         | 27  | 3   | 0.49  | 0.27  |  |
| Puffy LF       | 40 | 48  | 12 | 39         | 28  | 5   | 0.49  | 0.27  |  |
| Pyrite LF      | 17 | 21  | 62 | 15         | 11  | 4   | 0.61  | 0.29  |  |
| Bourneville LF | 10 | 11  | 79 | 9          | 8   | 5   | 0.66  | 0.30  |  |
| Steel LF       | 13 | 17  | 70 | 11         | 9   | 4   | 0.63  | 0.29  |  |
| Jet LF         | 7  | 8   | 85 | 6          | 5   | 4   | 0.68  | 0.30  |  |

Ts Solar Transmittance Rs Solar Reflection

As Solar Absorbance

G-Value % Solar Radiation through Fabric

Tv Visual Light Transmission G-Total % Solar

G-Total % Solar Radiation through Blind and Window

## Melbourne Head Office

Building 1, Level 2, 630 Mitcham Road Mitcham VIC 3132 Australia

P +61 3 9729 9970 E sales@texstyle.com.au Learn more at texstyle.com.au

