Dakota









Technical Data

Composition	30% polyester / 70% PVC					
Width	3,000mm					
Weight	413gsm +/-10%					
Thickness	0.72mm +/-5%					
Opacity/Openness	Approx. 6%					
Light Fastness	≥ 5 (Blue wool scale)					
Coating	Polyester yarns with PVC coating					
Flame Retardant	Product is designed and manufactured to comply with Building Code of Australia requirements for class 2 to 9 buildings					
Cleaning	Wipe clean with warm soapy water and damp cloth					















5 YEAR WARRANTY

SCREEN

FRIENDLY RETARDANT

Solar Properties

	USA Standard Tested To Ashrae 74-73											
							Shading Coefficients (Sc)					
	1	Гs	Rs	As	Tv/Vlt	0-F	3mm CL.	6mm CL.	9mm CL.			
Quartz	6	26	63	11	8	6	0.38	0.38	0.34			
Marble	(25	50	25	5	6	0.37	0.36	0.34			
Ore	(23	47	30	6	6	0.38	0.37	0.40			
Granite	7	7	4	89	7	6	0.74	0.70	0.51			
Flint	1	0	11	79	8	6	0.70	0.67	0.49			
Coal	3	3	4	88	8	6	0.74	0.70	0.51			

Ts Solar Transmittance Rs Solar Reflection

As Solar Absorbance

Tuv Ultraviolet Transmittance **O-F** Openness Factor

Tv Visual Light Transmission G-Value % Solar Radiation through Fabric

G-Total % Solar Radiation through Blind and Window